



TECHNICAL DATA SHEET

VISCOM EASYPRINT

Technical data sheet

VISCOM EASYPRINT

Certified for
HP Latex Inks

100%
PVC-free

Sizes in mm	2440 x 1220	3050 x 1530	3050 x 2030	4050 x 2030
Thicknesses in mm	5	10	15	19
Weight per m ²	1.70	1.84	2.01	2.14
Length – and Width tolerances in mm	-10.00	-10.00	-10.00	-10.00
Thickness tolerance in mm	+/-0.3	+/-0.3	+/-0.3	+/-0.3
Perpendicularity tolerance in mm (diagonal)	0.7 / 1000	0.7 / 1000	0.7 / 1000	0.7 / 1000

Facing sheet properties	Value	Unit	Standard
Tensile strength at yield	18	MPa	DIN EN ISO 527
Elongation at yield stress	4	%	DIN EN ISO 527
Tensile Modulus of elasticity	1800	MPa	DIN EN ISO 527-3/5/50
Impact resistance	no break	kJ/ m ²	DIN EN ISO 179
Shore hardness D	66	Shore	ISO 868
Extension of Length	80	10 ⁻⁶ / K	ISO 11359
Fire classification	B2	Euroclass	DIN 4102
Temperature range	-20 / +120	°C	-

XPS core properties	Value	Unit	Standard
Compressive stress: 10% compression	300	kPa	EN 826
Tensile strength	600	kPa	EN 1607
Water absorption during long-term immersion	1,5	%	EN 12087
linear thermal expansion coefficient	0,07	mm / (m x K)	-
Fire classification	E	Euroclass	DIN EN 13501-1
Temperature range	-50 / +75	°C	-

The data are guide values. The information on our products and their application possibilities corresponds to our current state of knowledge. This information does not guarantee certain properties of the products or their suitability for a specific application. We reserve the right to make changes in line with technical progress and developments.

For further information and application details please do not hesitate to contact our service department.

Available from Perspex Distribution

PERSPEX
Distribution Ltd

BLACKBURN: 01254 272 800
LEEDS: 01134 677 800
WEYBRIDGE: 01932 356 900

CHELMSFORD: 01245 232 800
TAMWORTH: 01827 263 900

STADUR
MADE IN GERMANY