

TYPICAL PHYSICAL PROPERTIES

PALSUN® Polycarbonate

Property	Test Method	Conditions	Units	Value
Physical				
Relative Density	ASTM D-792		g/cm ³	1.2
Water Absorption	ASTM D-570	24 hr @ 23°C	%	0.15
Mechanical				
Tensile Strength at Yield	ASTM D-638	10mm/min	MPa	65
Tensile Strength at Break	ASTM D-638	10mm/min	MPa	60
Elongation at Yield	ASTM D-638	10mm/min	%	6
Elongation at Break	ASTM D-638	10mm/min	%	>90
Tensile Modulus of Elasticity	ASTM D-638	1mm/min	MPa	2,300
Flexural Modulus	ASTM D-790	1.3mm/min	MPa	2,600
Flexural Strength at Yield	ASTM D-790	1.3mm/min	MPa	100
Izod Impact Strength	ASTM D-256	notched	J/m	800
Charpy Impact Strength	ASTM D-256	notched	J/m	800
Impact Falling Weight	ISO 6603	3mm sheet	J	158
Rockwell Hardness	ASTM D-785		R Scale	125
Thermal				
Service Temperature			°C	-50 to + 100
Heat Distortion Temperature	ASTM D-648	Load: 1.82MP	°C	130
Vicat Softening Temperature	ASTM D-1525	Load: 1kg	°C	150
Coefficient of Thermal Expansion	ASTM D-696		mm/m°C	0.065
Thermal Conductivity	C-177		W/m°K	0.21
Specific Heat Capacity	C-351		kJ/kg°K	1.26
Optical				
Light Transmission	ASTM D-1003		%	89
Refractive Index	ASTM D-542			1.586
Yellowness Index	ASTM D-1925			<1
Haze	ASTM D-1003		%	<0.5
Electrical				
Dielectric Strength	ASTM D-149	500V/s	kV/mm	>30
Surface Resistivity	ASTM D-257	Keithley	Ω	5.1x10 ⁵

Other physical properties and values available on request.

PALSUN® Flammability

Standard	Classification
EN13501	B, s1, d0
UL Classified	V2 (File e221255)