

# Transprint Blockout Banner

Base Fabric	(DIN 60001)	Trade Mark Polyester
Warp/Weft		500d x 500d
Threads (per inch)	(DIN 53853)	28/28
Total Weight	(DIN 53352) BS3424	610 grs/m2 +/-20grs
Breaking Strength	(Din53354) BS3424	1850/1350 N/5cm
Tear Strength	(Din53356) BS3424	235/225 N
Temperature Resistance	(DIN 53361)	0 to 40%
Application		Solvent UV Ink Printing
Coating		PVC
Flame Retardant	(DIN 75200)	Self-extinguishing

The information provided on this data sheet represents typical physical properties and does not constitute a specification. No liability will be accepted for errors and omissions and under no circumstances shall Transprint be liable for any loss or injury arising directly or as a consequence of the publication of this data sheet. All Transprint vinyls are sold subject to our Conditions of Sales. Transprint also retains the right to change sizes and specifications of products without prior notice.

Economy laminated Frontlit membrane for general production use with solvent and UV curable inks. (Short to medium term), not recommended in very cold environment. Shelf life 6 months.

*All products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.*