

Transprint Laminated Banner

Base Fabric	(DIN 60001)	Trade Mark Polyester
Thickness (mm)		0.42 + 0.02
Warp/Weft		300d x 500d
Threads (per inch)	(DIN 53853)	18/12
Total Weight	(DIN 53352)	440 grs/m2 +/-20grs
Peel Strength (N)		28
Tensile Strength warp/weft	(DIN 53354)	450/400 N/30mm
Tear Resistance warp/weft	(DIN 53363)	100/150 N/30mm
Temperature Resistance	(DIN 53361)	0 to 45%
Application		Solvent Ink Printing
Coating		PVC
Flame Retardant	(DIN 75200)	Self-extinguishing

The information provided on this data sheet represents typical physical properties and does not constitute a specification. No liability will be accepted for errors and omissions and under no circumstances shall Transprint be liable for any loss or injury arising directly or as a consequence of the publication of this data sheet. All vinyls are sold subject to our Conditions of Sales. Transprint also retains the right to change sizes and specifications of products without prior notice.

Economy laminated Frontlit membrane for general production use with solvent and UV curable inks. (Short to medium term), not recommended in very cold environment.

All products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.

TRANSPRINT

www.perspex.co.uk